

6. (Amended) A process for producing a sponge cloth which is based on cellulose and has been provided with an internal reinforcement, which comprises

- (a) providing a mixture which includes cellulose dissolved in the N-oxide of a tertiary amine and water and also at least one pore former and fibers, [but not blowing agent,]
- (b) spreading the mixture onto a transportation belt,
- (c) passing the layer through a coagulation bath comprising a dilute aqueous amine oxide solution to dissolve out the pore former,
- (d) washing the remaining amine oxide out,
- (e) drying the sponge cloth web and
- (f) end-iteming it
- (g) wherein said mixture is not exposed to conditions where a blowing agent decomposes to form gaseous products.

7. (Amended) A process for producing a sponge cloth which is based on cellulose and has an internal reinforcement, which comprises

- (a) providing a mixture which includes cellulose dissolved in the N-oxide of a tertiary amine and water and also at least one pore former,
- (b) applying the mixture to both sides of a polymeric net,
- (c) passing the layer through a coagulation bath comprising a dilute aqueous amine oxide solution to dissolve out the pore former,
- (d) washing the remaining amine oxide out,

(e) drying the sponge cloth layer and

62 (f) end-iteming it

(g) wherein said mixture is not exposed to conditions where a blowing agent decomposes to form gaseous products.

---